





LAMINATING SCREW

Originally designed for temporary drywall to drywall applications.
Also used to attach drywall to wood.



Meets
ASTM C-1002
Reduced #2 Phillips

Product Specifications



Part #	Dia.	Length	TPI	Bulk Qty	Finish	Head	Head Dia.	Corrosion	Thread	Point
LS10112	10	1-1/2	8	5M	Phos.	Bugle	8.5mm ~ 9.2mm	48 hr. min. B-117	Single lead	Piercing 25°

Pro-Twist Marker® Multi-Purpose Screws Meet or Exceed ASTM C-1002 and/or ASTM C-1513

Laminating Self-Piercing Point Screws Ultimate Values					
Dia.	Pull-Out 2x4 Red Wood	Pull-Out 3/4 Particle Board	Pull-Out 2x4 Fir	Pull-Out Plywood	Minimum Torsional Strength (Lb)
10	587	388	563	466	56

Ultimate Value Charts

Wood - Screws driven 3/4" into the wood material, then pulled out the testing machine.

Note that all results were obtained in strict adherence to ASTM test protocol. These ultimate figures are offered only as a guide and are not guaranteed in any way by PrimeSource. A 4:1 safety ratio is recommended.

Installation Guidelines

0-2500rpm Screwgun with torque adjustment - Overdriving may result in fastener failure or stripout of the work surface

The fastener is fully seated when the head's bearing surface is flush with the drywall

NOT Recommended for use with treated wood.

ALL PRIMESOURCE FASTENERS ARE MANUFACTURED IN AN ISO 9002 AND ISO 14001 CERTIFIED AND APPROVED FACTORY TO PRIMESOURCE PERFORMANCE SPECIFICATIONS AND PRINT DRAWINGS.